

FlowStone Specification Help



Stone Surfacing for Exterior Applications

Description

FlowStone™ is a thermal set 2 part UV stable polyurethane resin blended with a design mix of aggregates (typically 8mm-10mm) to create a continuous flexible stone surfacing system.

Uses

FlowStone™ is ideal for urban tree pits, pedestrians and light vehicular use on footpaths, courtyards and anywhere permeability is required.

Suitable Surfaces

FlowStone™ is designed to overlay well compacted free draining soils and aggregates, as well as on concrete or asphalt substrates. It is also available as a fully permeable surface over a crushed rock base.

Refer to Overlay of Asphalt and Concrete Specification Advice Sheets or Permeable Pavement Specification Advice Sheets for more detail.

Safety

For detailed information refer to the Material Safety Data Sheet.

Wearing of gloves, goggles, overalls, and safety footwear is highly recommended.

Surface Preparation

All areas to be treated shall be well constructed layers of free draining material to local design specifications and performance requirements.

DECORATIVE PAVING SPECIALISTS

All new concrete substrates must be subjected to a minimum curing period of 28 days. All concrete substrates must be primed with Rockseal Concrete Primer.

Mixing

A cement mixer is required to blend the bagged aggregate. The part A and B resin is then mixed in a separate mixing vessel using an electric drill and paddle.

Resin mix is then added to the cement mixer and combined with the aggregate. Once mixed it is dispensed to a wheelbarrow and taken to the work site ready for troweling.

Storage

All resins and aggregates must be stored in a clean and dry environment.

Refer to storage instructions and use by date on kit for details.

Yes, the finish can be rejuvenated by applying a topcoat of resin.

Application

FlowStone™ is hand trowel applied by trained and accredited applicators. Dispense mixed material. An asphalt rake, lute or gauge rake may be used to assist an even spread of material. Material should be trowel compacted to an even consistency and level.

The trowel should be regularly wiped clean to avoid resin build up and to achieve best results. At this stage, when required, dust with glass for anti-slip finishes. Repeat process to completion.

Do not walk on surface until completely set and tack free.

Do not traffic surface with vehicles for 3 days.

Clean Up

White spirits is used for clean-up.

Coverage

Depth	Approx Coverage
15mm	27 kg/m ²
20mm	40 kg/m ²
30mm	54 kg/m ²

Technical Data

Standard Pack Size

80kg kit of Resin and Aggregate

Other kit sizes available

Application Conditions

- Ground temperatures 5-45°C
- No rain, showers or ambient humidity above 90%
- Not beyond Dew Point (refer to dew point calculator)
- Damp or wet surface

Performance Properties

Tensile Strength: 100Kn/m

(When used with Fibre grid)

UV Stability: 60°gloss > 90% @ 5yr

(ASTM D523 Florida Gloss Retention)

Permeability: 1000-1500mm/min.

(AS/NZS 4456.16:1997)

DECORATIVE PAVING SPECIALISTS