

AZZURRA



SUPER-WASHABLE ACRYLIC WATER-PAINT FOR INTERIORS AND EXTERIORS Compliant with the directive 2004/42/CE

DESCRIPTION

Acrylic water-paint super-washable of excellent quality for interiors and exteriors, with an high covering power, thixotropic, breathable, anti-mold, excellent whiteness, resistant to alkalis and to washings.

COLOR

White and color chart.

PACKAGING

Lt. 4 – 14 Plastic containers.

COMPOSITION

Based on acrylic resins in aqueous dispersion, selected aggregates, inorganic pigments inalterable over time and additives tested to improve the workability.



USE

For the internal and external painting of surfaces both old and new as float plasters based on gypsum and on cement, walls skim coated with stucco, plasterboard, wallpapers, wood and generally non-ferrous substrates. Perfect for re-painting.

TECHNICAL SPECIFICATIONS

Specific Weight $\pm 5\%$ UNI EN ISO 2811-1	1,600 Kg/lt
Dry residue UNI EN ISO 3251	71%
PH	≥ 8
Viscosity	$\sim 50.000\text{mPa}\cdot\text{s}$
Minimum Temp. for the film formation	$+5^\circ\text{C}$
Theoric yield	12/14 mq/lt for each coat
Limit value UE of the content of VOC (2010)	$\leq 30\text{ gr/lt}$
Content of VOC	$\leq 15\text{ gr/lt}$
Classification DIRECTIVE 2004/42/CE	A/BA

APPLICATION

- Prepare the substrates, both old and new, making sure that are perfectly dried and clean, removing all the crumbling and inconsistent parts and dusts, mud, bitumen, oil stains, etc.
- Brush carefully any old paints not adherent to the substrate.
- Make sure that the substrates are free of saline efflorescence and stains of active humidity.
- Make a first coat of preparation of the ground with an insulating primer with an high penetration "PREVIT" diluted with clean water up to a ratio 1:5 depending on the absorption of the substrate.
- Inside to make a partial plastering or a complete skim coating after 6/12 hours at least with "MALVISTUK" paste stucco or "MICRORAS SB" powder stucco for interiors.
- Outside, if necessary, to make a partial plastering or a complete skim coating after 6/12 hours at least with "INTORAS M or MC" powder stucco for exteriors.
- Then apply a coat of primer "PREVIT" to uniform the absorption diluted with clean water up to a ratio of 1:5 depending on the absorption of the substrate.
- Then apply a first layer of product diluted at 50/55% in volume for each coat.



- Then apply a second coat of the product diluted at 40/45% in volume with clean water.
- Apply with a roller on the same way.
- Waiting time between the first and the second coat 6 hours at least.
- Don't apply on frozen substrates, with frost or possible frost in 24 hours.
- Don't apply until when the substrate hasn't completely dried.
- Don't apply in very sunny days.
- Don't apply with strong wind and/or driving rain.
- We suggest to apply AZZURRA with a temperature between + 5 ° C and + 30 ° C.

FILM FEATRES

Uniform and with a slightly satin finish, super covering, super-washable, a very high adhesion and resistance, an excellent dilatation, breathable, water-repellent, anti-mold, antibacterial.

DILUTION

From 40 to 55% in volume with clean water; with a roller ready to use.

USE

Brush, spray and roller.

DRYING TIME

About 5 hours to the touch.

COMPATIBILITY

With every product based on resins in aqueous dispersion.

SUMMARY

The protection and the decoration for interiors and exteriors will be realized with a breathable super-washable water-paint for interiors and exteriors, based on acrylic resins, type "AZZURRA" by MALVIN S.r.l. , applied in two coats with a brush or by spray dilution from 40 to 55% in volume with clean water; with a roller ready to use, with a yield of 12/14mq/tl for ech coat, on surfaces previously treated with primer "PREVIT".

MALVIN

The performance characteristics refer to laboratory tests, values depend on the weather conditions and on the method of implementation. The user must verify that the product is suitable for the intended application.



MALVIN

