

### V-104 GLOSS BLACK HI SOLIDS DIPPING ENAMEL

PRODUCT DESCRIPTION: V-104 Gloss Black Dipping Enamel is an exceptional and durable interior/exterior alkyd gloss dipping enamel, for general maintenance painting and new construction. Formulated with special pigments and resin for excellent adhesion, and weathering resistance.

INTENDED USES: V-104 is formulated for use on properly prepared substrates such as metal. Its primary use is a fast dry dipping enamel, where a high gloss, quality product is desired for extended durability. Other intended uses are for ornamental ironwork, and structural steel.

SURFACE PREPERATIONS: For best results it is important that all surface contaminants, such as

moisture, oil, dirt, rust and mill scale be removed before application. V-104 can be applied to either blasted, hand or power tool cleaned steel. A minimum of SSPC-2 hand tool cleaning required.

### PHYSICAL INFORMATION

COLOR: BLACK GLOSS: GLOSS

**SOLIDS BY WEIGHT: 63%** 

**RECOMMENDED DRY FILM THICKNESS:** 1.5-2.0 MILS **THEORETICAL COVERAGE:** 400-450 SQ FT PER GALLON

METHOD OF APPLICATION: DIPPING, AIRLESS SPRAY, AIR SPRAY

### DRYING TIME @ 72 F

TO TOUCH: 30 MINUTES
TO HANDLE: 60-90 MINUTES

**TO RECOAT:** WITHIN 6 HOURS OR AFTER 5 DAYS.

# REGULATORY DATA

**FLASHPOINT:** 63 F

**PRODUCT WEIGHT: 9.40 LB** 

MATERIAL VOC: 3.10 POUNDS PER GALLON / 372 GRAMS PER LITER COATING VOC: 3.41 POUNDS PER GALLON / 409 GRAMS PER LITER



## **APPLICATION**

MIXING: This material is a one-component coating and should always be mixed thoroughly with a power agitator

before application.

MIX RATION: Not applicable

WORKING POT LIFE: Not applicable

**AIRLESS SPRAY: Suitable** Tip Range 15-17 thou (0.38-0.43mm)

total output fluid pressure at spray tip not less

than 2,500 P.S.I.

AIR SPRAY: Suitable Gun DeVilbiss MBC or JGA

(Pressure Pot) Air Cap 704

Tip E

**BRUSH: Suitable** Typically 1.5-2.0 mils can be achieved. Care

should be taken to avoid under application.

**ROLLER: Suitable** Typically 1.5-2.0 mils can be achieved. Care

should be taken to avoid under application.

**THINNER:** Xylene Do not thin more than allowed by local

environmental legislation when applicable.

**CLEANER:** Xylene

WORK STOPPAGES: Thoroughly flush all equipment with xylene. All unused material should be stored in tightly closed containers. Partially filled containers may show surface skinning and/or viscosity increase of the material after storage. Material should be filtered prior to use.

**CLEAN UP:** Clean all equipment immediately with xylene. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.

All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations legislation.

### SYSTEM COMPATIBILTY:

The following primers are recommended for this topcoat

Shop Coat Alkyd Primers

**Universal Phenolic Primers** 

SHIPPING & STORAGE

**NUMBER OF COMPONENTS:** 

PACKAGED IN: 55-Gallon Drums, 5 Gallon Pails, and 1 Gallon Cans.

STORAGE TEMPERATURE: Minimum 20 F. Maximum 110F