

Artigiana Graniti s.n.c.

**Strada Provinciale 166 della Valle Ossola, 1
28803 PREMOSELLO CHIOVENDA (VB)
tel. +39 0324 80116 – fax +39 0324 80270
e-mail: info@artigianagraniti.it**

EN 1343


BEOLA GRIGIA

Trontano, VB, Italia

Uso: Cordoli e bordure di pietra naturale

Rilascio di sostanze nocive	NPD
Resistenza a flessione (EN 12372, valore medio) perpendicolare ai piani di anisotropia	14,7 MPa
Resistenza allo scivolamento (EN 14231), superficie levigata grossa - taglio diamante	62
Resistenza al flessione dopo cicli di gelo/disgelo (EN 12371)	13,3 MPa
Resistenza al gelo/disgelo in presenza di Sali antigelo (SIA 262/1 C)	Alta resistenza

NPD = nessuna prestazione determinata / No performance determined



Artigiana Graniti s.n.c.

**Strada Provinciale 166 della Valle Ossola, 1
28803 PREMOSELLO CHIOVENDA (VB)
tel. +39 0324 80116 – fax +39 0324 80270
e-mail: info@artigianagraniti.it**

EN 1343

BEOLA GRIGIA

Trontano, VB, Italy

Use: Kerbs of natural stone

Release of dangerous substances	NPD
Flexural strength (EN 12372, mean value) perpendicular to the planes of anisotropy	14,7 MPa
Slip resistance wet (EN 14231) Honed finish - diamond disc finish	62
Durability of flexural strength against freeze/thaw (EN 12371)	13,3 MPa
Freeze/thaw with de-icing salts (262/1)	Alta resistenza

NPD = nessuna prestazione determinata / No performance determined