

370HP







370HP geotextile is composed of high-tenacity monofilament polypropylene yarns, which are woven into a network such that the yarns retain their relative position. 370HP geotextile is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Our Laboratories are accredited by <u>a2La</u> (The American Association for Laboratory Accreditation) and Geosynthetic Accreditation Institute – Laboratory Accreditation Program (<u>GAI-LAP</u>). NTPEP Listed

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D4595	lbs/ft (kN/m)	3600 (52.5)	3240 (47.3)
Tensile Strength (at 5% strain)	ASTM D4595	lbs/ft (kN/m)	1500 (21.9)	1560 (22.8)
Flow Rate	ASTM D4491	gal/min/ft ² (l/min/m ²)	40 (1630)	
Permittivity	ASTM D4491	sec ⁻¹	0.9	
			Maximum Opening Size	
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	40 (0.425)	
			Minimum ⁻	Test Value
Pore Size 0 ₉₅ 1	ASTM D6767	microns	292	
Pore Size 0 ₅₀ ¹	ASTM D6767	microns	158	
Factory Sewn Seam	ASTM D4884	lbs/ft (kN/m)	2400 (35.0)	
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	80	

¹ Based on Third Party Testing

Physical Properties	Unit	Roll Size / Weight	
Roll Dimensions (width x length)	ft (m)	15 x 300 (4.5 x 91)	
Roll Area	yd² (m²)	500 (418)	

Disclaimer: L & M Supply assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. L & M Supply adisclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

L & M Supply Co., Inc.
P. O. Box 640 - Willacoochee, GA 31650
912-534-6071 Direct
800-948-7870 Toll Free
912-534-6254 Fax
www.landmsupplyco.com



GAI-LAP-25-97



